

Permissable Glass Sizes

Glass thickness (mm)	Maximum area of glass (m ²)	Maximum length of side (mm)	Minimum space between glass (mm)	Maximum ratio of sides
3	1.5	1500	10	1 ; 6
4	2.5	2500	10	1 ; 6
4	3.35	2500	12	1 ; 10
5	3.5	3000	10	1 ; 10
5	5	3300	12	1 ; 10
6	4.5	3000	10	1 ; 10
6	7	3500	12	1 ; 10
8	6	3000	10	1 ; 10
8	8,75 *	3500	12	1 ; 10
8	10 *	5000 *	16	1 ; 10
10	13,50 *	5000 *	16	1 ; 10

* glass must be toughened

In cases where a double glazed unit is made with different combinations of thickness of glass, then acceptable sizes of glass are defined by the minor glass thickness.